

# VISA PREMIUM

## Special opaque wood stain

Water-borne, hybrid binder based opaque wood stain with long maintenance interval for outdoor use. The hybrid binder of VISA PREMIUM combines acrylate and alkyd to create a modern and highly durable product. Easily spreading VISA PREMIUM gives an opaque protection while leaving the surface texture of the wood visible. Gives a water-resistant but well breathable surface. Finish: gloss.

To be used for renewed treatment of old, faded wood stain surfaces, and also when a uniform colour is desired on old and new wood stain surfaces. Suitable also for use on new and press-impregnated wood, for log surfaces as well as for maintenance painting on acrylate paints. Typical objects are walls, covering boards, fences, window frames, etc.



### TECHNICAL DATA

<b>Certificates, approvals and classification</b>	Finnish Key Flag
<b>Fields of application</b>	Cladding boards, Fences, Outdoor wall
<b>Recommended substrate</b>	Acrylate paint, Fine-sawn wood, Log, Oil paint, Planed wood, Pre-primed boards, Wood stain
<b>Solids</b>	Approx. 32% by volume
<b>Volatile organic compound (VOC)</b>	EU VOC limit value (kat A/e): 130 g/l. The product's VOC: max. 130 g/l.
<b>Practical spreading rate</b>	Sawn timber: 6 - 8 m <sup>2</sup> /l. Planed timber: 9 - 11 m <sup>2</sup> /l.
<b>Tinting system</b>	Teknomix
<b>Gloss (60°)</b>	Gloss
<b>Thinner</b>	Water.
<b>Density</b>	Approx. 1.2 g/ml
<b>Storage</b>	Must be stored tightly closed and kept cool. Must not freeze.
<b>Packaging</b>	Base paints 1 and 3: 0.9 l, 2.7 l, 9 l.

## DIRECTION FOR USE

### Surface preparation

#### NEW WOODEN SURFACES:

Treat the surface as soon as possible. At least the impregnation and priming would be best done in the summer of construction.

Remove from the surface all loose matter, dirt, dust and mildew. If needed, use RENSA FACADE facade cleaner.

#### PREVIOUSLY PAINTED/WITH PRIMING OIL TREATED OR OLD WOODEN SURFACES:

Change deteriorated wooden parts with new ones. Remove loose matter, loose or poorly adherent paint or priming oil as well as greyed or fluffy layers of wood by e.g. scraping, wire brushing or using an infra-red heater. Avoid unnecessary damaging of the wooden surface. Note, that the adhesion of an old thick paint layer to the substrate may have been weakened, therefore the paint should be removed although the paint film looks intact. The surface of old oil paint coats may be in poor condition: heavily chalked, dusty and brittle. These types of surfaces must be carefully cleaned so, that the new paint adheres properly to the substrate. Some traditional paint types, such as red ochre paint and paraffin oil paint, produce such a brittle and dusty surface, that they can't be maintenance painted with this product. If there is doubt about the adhesion, it must be ensured by test painting.

Wash surfaces with RENSA FACADE facade cleaner. Avoid unnecessary wetting of the wooden structures during the washing.

### Priming

Coat untreated wooden surface with clear wood preservative from the WOODDEX series. Allow to dry for one day.

The surface treated with priming oil is then primed with VISA PREMIUM. For priming the product can be diluted max. 10 %. Allow to dry for abt. 12 h. Treat end grain especially carefully.

### Application method

Brush, Spray

If the product is applied by airless spray, the surface is to be finished by a brush to ensure the adhesion. Recommended airless spray nozzle is 0.015–0.021".

### Application

Reserve a sufficient amount of paint in the same vessel for each uniform surface. Colour differences will thus be avoided.

Stir thoroughly before use.

Primed or previously painted surfaces are top coated 1–2 times depending on the coarseness of the surface, the colour of the substrate and/or the the coverage of the colour. Avoid overly thick paint films on log surfaces.

<b>Application conditions</b>	The surface to be treated must be dry. The moisture content of the wood is to be below 20%. During the application and drying period the temperature of the ambient air, the surface and the product shall be above +5 °C and the relative air humidity below 80%. Avoid application in direct sunlight.
<b>Drying time</b> <b>- overcoatable</b>	+23 °C / 50% RH 12 h The drying process will be slower in cold and/or damp.
<b>Resistance</b>	Weather resistance: Good.
<b>Cleaning</b>	Warm water and RENSA BRUSH brush cleaner. Wash the equipment immediately after use.

## HEALTH AND SAFETY

**Safety and precaution measures** See safety data sheet.

**Teknos Group Oy Takkatie 3, P.O.Box 107 FI-00371 Helsinki, Finland Tel. +358 9 506 091**

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com). All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.